

**Conley Product Data**

**OUTSTANDING BENEFITS AND COST SAVINGS**

**Description**



- Heavy duty filament wound piping for service up to 250 psi
- 60 mil double Nexus® reinforced corrosion barrier (inner liner)
- Premium aromatic amine cured product for operating temperatures up to 275°F
- Sizes available from 2" through 30"
- Complete line of filament wound fittings available
- In house fabrication facilities "From your blueprints to pipe assemblies"
- Color coding available
- Conductive systems available
- Fire-resistant systems available
- See Sch 30 Piping Specification

**Typical Applications**

- Waste water treatment
- Steel pickling
- Solvents
- Petrochemical
- Pharmaceutical
- Chemical processing
- Brine (salts) and brackish water
- Jet fuel
- Gasoline – Diesel – Fuel Oil
- Cooling water
- Odor control
- Industrial waste
- Food and beverages
- Bridge, roof and floor drains

**Performance**

- Excellent chemical resistance inside and outside to a variety of caustics and acids ~ See the chemical resistance chart for fluid services
- External UV/Corrosion barrier minimum 10 mil on all pipe and fittings
- 25 year guarantee against *'fiber blooming'* on all pipe and fittings
- Straight socket joining system (No expensive tapering tools required)

**Specifications**

- ASTM D2996 Filament-Wound "Fiberglass" Pipe
- ASTM D2310 Classification for Machine-Made "Fiberglass" Pipe
- ASTM D3567 Determining Dimensions of "Fiberglass" Pipe and Fittings
- ASTM D4024 Machine Made "Fiberglass" Flanges
- ASTM D5685 "Fiberglass" Pressure Pipe Fittings

**Codes & Standards**

- AWWA C950 Fiberglass Pressure Pipe Standards
- ASME B31.1 Power Piping Code
- ASME B31.3 Process Piping Code

**Listings**

- U.S. Federal Regulations FDA 21 CFR 175.300
- CRN:0A10216.5 Category A - Pipe Fittings
- CRN:0B10216.5 Category B - Pipe Flanges



**Schedule 30  
Pipe Dimensional Data\*  
and Pressure Ratings<sup>(1)</sup>  
from -50° to 275°F**

<sup>(1)</sup>Static pressure rating; steady (stationary) pressure is created when using a gear pump, turbine pump, centrifugal pump, etc.  
<sup>(2)</sup>Vacuum Service: A full vacuum within the pipe is equivalent to 14.7 psi external pressure at sea level. Contact Conley for higher external pressure ratings.



NOM PIPE DIA	PIPE I.D.	PIPE O.D.	NOM LINER THK (IN)	NOM REINF THK (IN)	NOM UV THK (IN)	TOT THK (IN)	INT PRESS (PSI)	VAC PRESS (PSI) <sup>(2)</sup>
2"	1.88	2.17	0.060	0.075	0.010	0.145	250	111.4
3"	3.00	3.34	0.060	0.090	0.020	0.170	250	52.8
4"	4.00	4.34	0.060	0.090	0.020	0.170	250	24.1
6"	6.00	6.38	0.060	0.110	0.020	0.190	175	13.8
8"	8.00	8.38	0.060	0.110	0.020	0.190	150	6.1
10"	10.00	10.49	0.060	0.165	0.020	0.245	150	10.2
12"	12.25	12.74	0.060	0.165	0.020	0.245	125	5.7
14"	14.25	14.78	0.060	0.165	0.040	0.265	100	3.6
16"	16.25	16.78	0.060	0.165	0.040	0.265	100	2.5
18"	18.25	18.85	0.060	0.220	0.020	0.300	100	4.2
20"	20.25	20.85	0.060	0.220	0.020	0.300	100	3.1
24"	24.25	24.96	0.060	0.275	0.020	0.355	100	3.5
30"	30.50	31.32	0.060	0.330	0.020	0.410	100	3.1

\*All values are nominal. Minimum wall thickness shall not be less than 87.5% of nominal wall thickness in accordance with ASTM D2996.

**Support Spans\* and Capacities at 75°F**



NOM PIPE DIA	TYPE I SIMPLE SPAN (FT)	TYPE II MAX CONT SPAN (FT)	TYPE IV FIXED END SPAN (FT)	MIN BEND RADIUS (FT)	WT/FT (LBS)	CAP (GAL/FT)
2"	8.6	10.1	12.9	44	0.74	0.14
3"	10.3	12.0	15.3	69	1.36	0.37
4"	11.4	13.3	17.0	93	1.79	0.65
6"	13.1	15.3	19.5	139	2.97	1.47
8"	14.4	16.9	21.5	185	3.93	2.61
10"	16.3	19.1	24.4	231	6.34	4.08
12"	17.3	20.3	25.8	284	7.73	6.12
14"	18.0	21.1	27.0	330	9.72	8.28
16"	18.7	21.9	27.9	376	11.05	10.77
18"	20.5	24.0	30.6	422	14.06	13.59
20"	21.1	24.7	31.5	469	15.57	16.73
24"	23.2	27.2	34.7	561	22.06	23.99
30"	25.7	30.1	38.4	706	32.01	37.95

\*NOTE: Span deflection = 1/2" with fluid of 1.0 specific gravity

**Span multipliers for fluids of different specific gravities**

FLUID SPECIFIC GRAVITY							
AIR	0.75	0.9	1.0	1.1	1.25	1.5	2.0
1.40	1.07	1.02	1.0	0.98	0.95	0.90	0.84
(MULTIPLIER FOR CORRECTED SPAN LENGTHS)							

**Span multipliers for fluids at different temperatures**

FLUID TEMPERATURE						
75°F	100°F	150°F	200°F	225°F	250°F	275°F
1.0	0.98	0.93	0.88	0.84	0.80	0.75
(MULTIPLIER FOR CORRECTED SPAN LENGTHS)						

## Typical Properties

TEMPERATURE	75°F	250°F	
PROPERTY	VALUE	VALUE	METHOD
AXIAL TENSILE STRENGTH	14,200 psi	10,650 psi	ASTM D2105
AXIAL TENSILE DESIGN STRENGTH	3,550 psi	2,660 psi	ASTM D2105
AXIAL MODULUS OF ELASTICITY	1.75 x 10 <sup>6</sup> psi	1.30 x 10 <sup>6</sup> psi	ASTM D2105
COMPRESSIVE STRENGTH	22,750 psi	17,000 psi	ASTM D695
COMPRESSIVE DESIGN STRENGTH	5,685 psi	4,250 psi	ASTM D695
COMPRESSION MODULUS	2.80 x 10 <sup>6</sup> psi	2.10 x 10 <sup>6</sup> psi	ASTM D695
POISSON'S RATIO $V_{a/h}$ ( $V_{h/a}$ )	0.33 (0.23)		*CONLEY METHOD #20
BEAM BENDING, ULTIMATE STRESS	30,000 psi	22,500 psi	CONLEY METHOD 8
BEAM BENDING, DESIGN STRESS <sup>(1)</sup>	3,750 psi	2,810 psi	CONLEY METHOD 8
SHEAR MODULUS	1.30 x 10 <sup>6</sup> psi	1.00 x 10 <sup>6</sup> psi	*CONLEY METHOD #9
HYDROSTATIC DESIGN BASIS	16,000 psi	8,000 psi	ASTM D2992 PROCEDURE B
HYDROSTATIC BURST (WALL STRESS @ 72°F)	32,000 psi	24,000 psi	ASTM D1599
CIRCUMFERENTIAL MODULUS OF ELASTICITY	2.50 x 10 <sup>6</sup> psi	1.87 x 10 <sup>6</sup> psi	ASTM D1599
FLEXURAL MODULUS OF ELASTICITY	1.75 x 10 <sup>6</sup> psi	1.30 x 10 <sup>6</sup> psi	ASTM 2790
COEFFICIENT OF LINEAR THERMAL EXPANSION	9.5 x 10 <sup>-6</sup> IN/IN-°F		CONLEY METHOD 3
COEFFICIENT OF THERMAL CONDUCTIVITY	2.9 BTU/HR-IN/FT <sup>2</sup> -°F		CONLEY METHOD 16
SPECIFIC GRAVITY	1.85		
DENSITY	0.067 LB/CU IN		
DIELECTRIC STRENGTH	535 VOLTS/MIL		ASTM D149
DEGREE OF CURE	175°C (347°F) Tg		DMA
HEAT DEFLECTION TEMPERATURE	150°C (302°F)		ISO 75-3
FLOW FACTOR (HAZEN-WILLIAMS)	150		
SURFACE ROUGHNESS	1.7 X 10 <sup>-5</sup> FEET		
MANNING'S "n"	0.009 INCH		

<sup>(1)</sup>Beam bending design stress is 1/8 of ultimate to allow for combined stress (bending and pressure)



## Pipe Section Properties

<sup>(1)</sup>Use these values to calculate permissible spans.

<sup>(2)</sup>Use these values for calculating longitudinal thrust.

NOMINAL PIPE SIZE (IN)	REINFORCEMENT ONLY (STRUCTURAL CAGE)			TOTAL WALL END AREA (IN <sup>2</sup> ) <sup>(2)</sup>
	END AREA (IN <sup>2</sup> )	MOMENT OF INERTIA (IN <sup>4</sup> ) <sup>(1)</sup>	SECTION MODULUS (IN <sup>3</sup> )	
2	0.49	0.26	0.25	0.92
3	0.91	1.17	0.71	1.69
4	1.19	2.64	1.23	2.23
6	2.15	10.45	3.29	3.70
8	2.84	24.09	5.77	4.89
10	5.33	70.53	13.47	7.885
12	6.50	127.67	20.07	9.62
14	7.53	199.05	27.03	12.08
16	8.57	293.03	35.02	13.75
18	12.85	555.26	58.92	17.48
20	14.23	754.42	72.36	19.37
24	21.29	1617.13	129.52	27.44
30	32.09	3843.41	245.24	39.81



ISO 9001:2008  
CERTIFIED  
Conley  
Composites  
Tulsa,  
Oklahoma USA

This product data sheet and recommendations it contains are based on data reasonably believed to be reliable. It is intended that this data be used by competent personnel having acceptable training in accordance with current industry practice and operating conditions. Variation in environment, application or installation, changes in operating procedures, or extrapolation of data may cause unsatisfactory results. Conley Composites makes no representation or warranty, express or implied, including warranties of merchantability or fitness for purpose, as to accuracy, adequacy or completeness of the recommendations or information contained herein. Conley Composites assumes no liability whatsoever in connection with this literature or the information or recommendations it contains.



2795 East 91st Street  
Tulsa, Oklahoma 74137 USA  
Phone: (918) 299-5051 Fax:  
(918) 299-5907  
[www.conleyfrp.com](http://www.conleyfrp.com)  
E-Mail: [sales@conleyfrp.com](mailto:sales@conleyfrp.com)